

H360 规格书(Line-up)

基板 CCL: H360

半固化片 PP: H360P

1、Only E-Glass Type CCL: H360

Core Thickness		Standard Construction	RC (%)	Dk			Df		
mil	mm			1GHz	5GHz	10GHz	1GHz	5GHz	10GHz
2.0	0.051	1035X1	65	3.44	3.37	3.36	0.0022	0.0039	0.0042
2.0	0.051	106X1	71	3.29	3.23	3.20	0.0021	0.0037	0.0038
2.4	0.061	1067X1	70	3.31	3.24	3.22	0.0021	0.0038	0.0039
2.6	0.066	1080X1	57	3.65	3.58	3.57	0.0022	0.0042	0.0047
		1078X1	57	3.65	3.58	3.57	0.0022	0.0042	0.0047
3.0	0.076	1078X1	63	3.50	3.43	3.41	0.0022	0.0040	0.0043
4.0	0.102	3313X1	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
		1035X2	65	3.44	3.37	3.36	0.0022	0.0039	0.0042
		106X2	71	3.29	3.23	3.20	0.0021	0.0037	0.0038
5.0	0.127	2116X1	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
		1080X2	57	3.65	3.58	3.57	0.0022	0.0042	0.0047
		1078X2	57	3.65	3.58	3.57	0.0022	0.0042	0.0047
6.0	0.152	1078X2	63	3.50	3.43	3.41	0.0022	0.0040	0.0043
		1080X2	63	3.50	3.43	3.41	0.0022	0.0040	0.0043
7.0	0.178	1078X2	68	3.38	3.31	3.30	0.0021	0.0039	0.0041
8.0	0.203	3313X2	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
10.0	0.254	2116X2	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
12.0	0.305	3313X3	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
16.0	0.406	3313X4	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
20.0	0.508	2116X4	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
25.0	0.635	2116X5	54	3.72	3.65	3.65	0.0023	0.0043	0.0048
30.0	0.762	2116X6	54	3.72	3.65	3.65	0.0023	0.0043	0.0048

2、Only E-Glass Type PP: H360P

GLASS Type	RC	Pressed Thickness		Dk			Df		
	%	mil	mm	1GHz	5GHz	10GHz	1GHz	5GHz	10GHz
1027	75	2.0	0.050	3.18	3.11	3.09	0.0021	0.0037	0.0037
1035	68	2.2	0.056	3.37	3.30	3.28	0.0021	0.0039	0.0041
	70	2.5	0.063	3.31	3.24	3.22	0.0021	0.0038	0.0039
	73	2.7	0.068	3.24	3.17	3.14	0.0021	0.0037	0.0038
	75	2.9	0.074	3.18	3.11	3.09	0.0021	0.0037	0.0037
106	72	2.1	0.053	3.26	3.19	3.17	0.0021	0.0037	0.0038
	75	2.4	0.060	3.18	3.11	3.09	0.0021	0.0037	0.0037
1067	72	2.6	0.066	3.26	3.19	3.17	0.0021	0.0037	0.0038
	75	2.9	0.075	3.18	3.11	3.09	0.0021	0.0037	0.0037
1080	64	3.0	0.076	3.47	3.40	3.38	0.0022	0.0040	0.0042
	68	3.5	0.089	3.37	3.30	3.28	0.0021	0.0039	0.0041
	70	3.7	0.095	3.31	3.24	3.22	0.0021	0.0038	0.0039
	72	4.0	0.102	3.26	3.19	3.17	0.0021	0.0037	0.0038
1078	64	3.0	0.077	3.47	3.40	3.38	0.0022	0.0040	0.0042
	68	3.5	0.089	3.37	3.30	3.28	0.0021	0.0039	0.0041
	70	3.7	0.095	3.31	3.24	3.22	0.0021	0.0038	0.0039
	72	4.0	0.102	3.26	3.19	3.17	0.0021	0.0037	0.0038
3313	54	4.0	0.102	3.73	3.66	3.65	0.0023	0.0043	0.0048
	57	4.2	0.106	3.65	3.58	3.57	0.0022	0.0042	0.0047
	59	4.4	0.111	3.61	3.54	3.51	0.0022	0.0041	0.0045
	61	4.8	0.122	3.55	3.48	3.46	0.0022	0.0041	0.0044
2116	54	5.0	0.126	3.73	3.66	3.65	0.0023	0.0043	0.0048
	56	5.2	0.132	3.68	3.61	3.59	0.0022	0.0042	0.0047
	58	5.5	0.138	3.63	3.56	3.54	0.0022	0.0041	0.0046

Remark: 1. The above data is for your reference only.

2. Please contact WAZAM sale and TS team if need more Laminates type.